# productinformation

## tesa<sup>®</sup> 4972 48μm double sided transparent filmic tape

tesa® 4972 is a transparent, double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive.

tesa® 4972 features especially:

- Thickness: 48µm
- High adhesion level
- Excellent resistance to demanding environmental conditions
- Excellent handling performance in converting processes

#### Main Application

- Mounting of metal or plastic badges and signs
- Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

#### Technical Data

<ul><li>Backing material</li><li>Color</li><li>Total thickness</li></ul>	PET film transparent 48 μm	<ul><li>Type of adhesive</li><li>Elongation at break</li><li>Tensile strength</li></ul>	tackified acrylic 50 % 20 N/cm
Adhesion to			
<ul> <li>Steel (initial)</li> <li>ABS (initial)</li> <li>Aluminium (initial)</li> <li>PC (initial)</li> <li>PE (initial)</li> <li>PET (initial)</li> <li>PP (initial)</li> <li>PS (initial)</li> <li>PVC (initial)</li> </ul>	7.0 N/cm 5.3 N/cm 5.2 N/cm 6.5 N/cm 3.1 N/cm 5.3 N/cm 3.0 N/cm 5.4 N/cm 5.7 N/cm	<ul> <li>Steel (after 14 days)</li> <li>ABS (after 14 days)</li> <li>Aluminium (after 14 days)</li> <li>PC (after 14 days)</li> <li>PE (after 14 days)</li> <li>PET (after 14 days)</li> <li>PP (after 14 days)</li> <li>PS (after 14 days)</li> <li>PVC (after 14 days)</li> </ul>	9.6 N/cm 6.5 N/cm 7.7 N/cm 8.6 N/cm 3.5 N/cm 7.0 N/cm 4.8 N/cm 7.1 N/cm 9.4 N/cm
Properties			

	Temperature resistance short term	200 °C		Resistance to chemicals	• • •
	Temperature resistance long term	100 °C		Softener resistance	
	Tack	• •		Static shear resistance at 23°C	
	Ageing resistance (UV)	••••		Static shear resistance at 40°C	••
•	Humidity resistance	••••			
E١	valuation across relevant tesa <sup>®</sup> assortme	nt: •••• very good	••	● good ●● medium ● low	

#### For latest information on this product please visit <u>http://l.tesa.com/?ip=04972</u>

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



en

great to work with

## tesa<sup>®</sup> 4972 48μm double sided transparent filmic tape

### Additional Information

Liner variants: PV20 brown/blue logo glassine paper (71µm; 82g/m<sup>2</sup>) PV43 white/blue logo PE-coated paper (122µm; 120g/m<sup>2</sup>)

For latest information on this product please visit <u>http://l.tesa.com/?ip=04972</u>

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

