productinformation

tesa® 62510

1000 µm double sided PE foam tape

tesa® 62510 is a double sided PE foam tape for mounting applications. It consists of a highly conformable PE foam backing and a tackified acrylic adhesive.

Product benefits:

- High ultimate adhesion level for a reliable bonding performance
- Fully outdoor suitable: UV, water and ageing resistant
- Conformable PE foam core with high inner strength
- Suitable for automatic and manual module assembly
- Easy solar module assembly due to a high foam compression rate

Main Application

- General mounting applications
- Mounting of trims and profiles
- Solar module frames

Technical Data

•	Backing material	PE foam	•	Type of adhesive	tackified acrylic
•	Color	black/white		Elongation at break	180 %
•	Total thickness	1000 μm	•	Tensile strength	10 N/cm

Adhesion to

•	Steel (initial)	13.5 N/cm	Steel (after 14 days)	13.5 N/cm
•	ABS (initial)	8.0 N/cm	ABS (after 14 days)	13.5 N/cm
•	Aluminium (initial)	8.0 N/cm	Aluminium (after 14 days)	13.5 N/cm
•	PC (initial)	8.0 N/cm	PC (after 14 days)	13.5 N/cm
•	PE (initial)	0.9 N/cm	PE (after 14 days)	0.9 N/cm
•	PET (initial)	6.0 N/cm	PET (after 14 days)	13.5 N/cm
•	PP (initial)	1.2 N/cm	PP (after 14 days)	1.2 N/cm
•	PS (initial)	8.0 N/cm	PS (after 14 days)	8.0 N/cm
•	PVC (initial)	13.5 N/cm	PVC (after 14 days)	13.5 N/cm

For latest information on this product please visit http://l.tesa.com/?ip=62510

tesa® 62510

1000 μm double sided PE foam tape

Properties

- Temperature resistance short term
- Temperature resistance long term
- Tack
- Ageing resistance (UV)
- Humidity resistance

- 80 °C Softener resistance
 - Static shear resistance at 23°C
 - Static shear resistance at 40°C
 - Static shear resistance at 70°C



Evaluation across relevant tesa® assortment: ••• very good •• good •• medium

Additional Information

Liner variants:

- PV0 brown glassine paper (71 μm)
- PV13 transparent PET film (50 μm)
- PV15 blue PE film (100 μm)

Peel Adhesion:

- immediately: foam splitting on steel
- after 14 days: foam splitting on steel, ABS, Aluminum, PC, PET, PS, PVC

tesa® 62510 is recognized by UL as photovoltaic polymeric material (QIHE2).

tesa® 62510 has been tested by TÜV Rheinland, Germany. The test confirms the longterm adhesion performance after IEC 61215 climate tests and a 85°C temperature resistance.

The temperature resistance (short/long) of tesa® 62510 has been approved according to tesa test method under static load.

Page 2 of 2 - As of 09/11/2018 -