productinformation

tesa HAF® 8401

200 μm amber reactive HAF mounting tape

tesa HAF® 8401 is a reactive heat activated film based on phenolic resin and nitrile rubber. This amber double sided tape has no backing. It is protected by a strong paper liner and can easily be slit and die cut.

At room temperature tesa HAF® 8401 is not tacky. It is activated for pre-lamination by heat and starts to become tacky at 90 °C. In a second application step heat and pressure is applied over a certain period of time.

After curing tesa HAF® 8401 reaches:

- Very high bonding strength
- High temperature resistance
- Excellent chemical resistance
- Bonds remain flexible and elastic

Main Application

It is suitable for bonding of all thermal resistant materials such as metal, glass, plastic, wood and textiles.

- High-strength splicing (overlap splice)
- Structural bonding
- Magnet bonding in electric motors
- Friction liners for clutches

Technical Data

:	Backing material	none amber		Bonding strength Shelf life time (packed) < 5°C	12 N/mm ² 18 months
	Total thickness			Shelf life time (packed) < 15°C	15 months
•	Type of adhesive	nitrile rubber / phenolic resin	•	Shelf life time (packed) < 25°C	12 months
	Type of liner	glassine			

tesa HAF® 8401

200 μm amber reactive HAF mounting tape

Additional Information

Processing:

1.Pre-lamination:

tesa HAF® 8401 is laminated before curing. For this process we recommend a temperature between 120 $^{\circ}$ C and 140 $^{\circ}$ C.

2. Bonding

The bonding conditions temperature, pressure and time depend on the application. Following parameters can be regarded as a guideline:

Splicing application:

Temperature: 120-220 °C

Pressure: >2barTime: 15 – 90 s.

Friction liners for clutches:

Temperature: 180 – 230 °C

Pressure: > 8 barTime: 3 min – 30 min

Magnet bonding:

Temperature: 140 – 180 °C
Pressure: > 6-10 bar
Time: 2 min - 5 min

Structural bonding:

Temperature: 180 – 220 °C
 Pressure: > 10-15 bar
 Time: > 3 - 30 min

Bonding strength values were obtained under standard laboratory conditions. Value is guaranteed clearance limit checked with each production batch (Material: Etched aluminium test specimen / Bonding conditions: Temp. = $120 \, ^{\circ}$ C; p = $10 \, \text{bar}$; t = $8 \, \text{min}$)

To reach maximum bonding strength surfaces should be clean and dry. Storage conditions according to tesa HAF® shelf life concept.

Page 2 of 2 - As of 15/11/2018 -