

PPI Adhesive Products Limited Waterford Industrial Estate Cork Road Waterford, Ireland. Phone: +353 (0) 51 590400 +353 (0) 51 377687 Fax: Email: info@ppi.ie Internet: www.ppi.ie



PPI – PRODUCT INFORMATION

PPI SP-2896-C BLACK OPAQUE DOUBLE SIDED **POLYESTER BASED SELF-ADHESIVE TAPE**

DESCRIPTION:

PPI SP-2896-C IS A POLYESTER BASED TAPE, COATED ON BOTH SIDES WITH A BLACK POLYACRYLATE SYTHECTIC RESIN ADHESIVE. ONE SIDE HAS BEEN SPECIFICALLY DEVELOPED TO COMBINE HIGH TACK, HIGH SHEAR AND HIGH ADHESIVE PEEL STRENGTH. IDEALLY SUITED FOR BONDING TO DIFFICULT SURFACES AND MATERIALS. PPI SP-2896-C IS SUPPLIED ON A BROWN PAPER INTERLINER.

APPLICATION:

- POSITIONING OF COMPONENTS •
- AUTOMOTIVE FIXTURES •
- AUTOMOTIVE LIGHTING

CONSTRUCTION:

	ADHES	IVE		
POLYESTER FILM				
ADHESIVE				
PAPER INTERLINER				
TECHNICAL DATA:	EN VALUES*:	ASTM VALUE**:	TEST METHO	DD:
SUPPORTING BASE:	POLYESTER FILM			
BASE THICKNESS: TOTAL THICKNESS:	0.025 mm 0.130 mm	1.00 MIL 5.20 MIL	BS 3924 BS 3924	
ADHESIVE TYPE:	POLYACRYLATE SYNTHETIC RESIN			
ADHESIVE STRENGTH:				
20 Mins Dwell - LINER SIDE UNWIND SIDE	4.0 N/cm 6.0 N/cm	36.0 OZ/INCH 54.0 OZ/INCH	ASTM D 1000 ASTM D 1000	
24 Hours Dwell - LINER SIDE UNWIND SIDE	5.0 N/cm 8.0 N/cm	45.0 OZ/INCH 72.0 OZ/INCH	ASTM D 1000 ASTM D 1000	
EPDM FOAM - 20 Mins Dwell EPDM FOAM - 24 Hours Dwell	1.5 N/cm Destructs Foam Upon Ren	13.5 OZ/INCH moval		
PMMA LENS – 20 Mins Dwell PMMA LENS – 24 Hours Dwell	4.0 N/cm 5.0 N/cm	36.0 OZ/INCH 45.0 OZ/INCH		
TENSILE STRENGTH: ELONGATION:	40.0 N/cm 80-120 %	23.0 LBS/INCH 80-120%	EN 60454 EN 60454	
COLOUR: HEAT CLASS: INTERLINER: INTERLINER RELEASE FROM TAPE:	BLACK OPAQUE B (TEMPERATURE RANGE UP TO 130°C/266°F) RELEASE COATED SILICONE BROWN PAPER			
Liner Side Unwind Side	0.10 N/cm 0.05 N/cm	0.90 OZ/INCH 0.45 OZ/INCH		
* EN 60454 / ** ASTM D-1000		· · · · · · · · · · · · · · · · · · ·		Rev.002/TF 01.Dec.17.

Statements, technical information and recommendations contained herein are based on tests we believe to be reliable but they are not to be construed in any manner as warranties expressed or implied The user shall determine the suitability of the product for the intended use and user assumes all risk and liability whatsoever therewith. Page 1 of 1